



SPECIALITY COATINGS

WOODCOTE HIGH SOLIDS NC WHITE PRIMER

CODE:	2601
DESCRIPTION:	Nitro Cellulose based white wood primer
PRODUCT:	WoodCote High Solids NC White Primer
Pack size:	5LT, 20LT, 200LT
Colour:	White
Gloss:	Matt
Substrate:	For sealing all types of softwood and hardwood including veneers and MDF.
Preparation:	Sand timber or MDF with 220 grit paper.
Pot Life:	N/A
Application:	Conventional spray, Airless, Air assisted, Dip.
Film Thickness:	Approx. 30 micron.
DRYING TIME:	
Surface Dry:	Touch Dry 15 minutes
Hard Dry:	To Sand 30 minutes
	It should be noted that these indicated times can vary considerably with changes in ambient temperatures can film build. Above times are at 25°C.
FORCE DRY:	Approx. 50°C.
RECOATING:	Refer to Technical Department.
SPREADING RATE:	6 - 8m ² / LT
THINNER/THINNING RATIO:	1:1 with Premium Lacquer Thinners
TECHNICAL DATA:	
Mass Solids:	± 36%
Volume Solids:	± 16%
Specific Gravity:	± 1,03
Binder Type:	Nitrocellulose
Application Viscosity:	20" F4 when thinned 1:1 with Premium Thinners
Health & Safety:	Refer Material Safety Data Sheet.

